

PRODUCT' SPECIFICATION

SK H2O protec construction waterstop series AA corners A & W according to DIN 18541, part 1 and 2, is a permanently flexible sealing profile made of thermoplastic polymer, PVC-P or PVC-NBR, that is used to seal construction joints in waterproof concrete structures with high water pressures.

Characteristics / Advantages

- high tensile strength and elongation at break
- high permanent flexibility and high-load bearing capacity
- suitable for water pressure and large settlings
- resistant to all natural media acting aggressively to concrete (if applicable)
- resistant to a wide range of chemical substances (tests required for each additional specific situation)
- standard resistant
- supply of systems for easy handling on site
- weldable by using butt joints on site

Application

- joint sealing in concrete structures
- construction joint sealing system for in-situ concrete

Typical structures

commercial buildings, cellars, underground car parks

Page 1/5 Version 10-2018



Standards / Directives

- DIN 18197
- DIN 18541, part 1 and 2
- WU- Directives DAfStb
- Welding instructions

Test certificate / Approvals

- latest manufacturer's test certificate
- certificate of conformity DIN 18541
- external monitoring by MPA NRW
- internal monitoring

PRODUCT DATA

Material

- PVC-P (Polyvinyl chloride with plasticizer / P: plasticized)
- PVC-NBR (Polyvinyl chloride Nitrile butadiene rubber)

Colour

black

Packaging

• supplied as standard rolls (25 m), pre-cuts and systems

Page 2 / 5 Version 10-2018





MECHANICAL PROPERTIES according to DIN 18541, part 2	
Shore A hardness	67 ± 5
Tensile strength	≥ 10 MPa
Elongation at break	≥ 350 %
Tear propagation resistance	$\geq 12 \text{ kN/m}$
Low temperature performance	Elongation at break at -20°C ≥ 200%
Performance after weathering	Tensile strength $\leq 20\%$ Elongation at break $\leq 20\%$ Modulus of elasticity $\leq 50\%$
valid change of average values relative to the initial value	
Performance of the weld at shear test short-term joining factor \mathfrak{f}_z	break outside of weld ≥ 0.6
Fire behaviour	class E
Performance after storage in bitumen	Tensile strength < 20% Elongation at break < 20% Modulus of elasticity < 50%

Page 3 / 5 Version 10-2018





AA 240 DIN Ecke A





AA 240 DIN Ecke W







All dimensions in mm

Page 4 / 5 Version 10-2018





AA 320 DIN Ecke A





AA 320 DIN Ecke W





All dimensions in mm

Page 5 / 5 Version 10-2018