

PRODUCT' SPECIFICATION

SK H2O protec construction waterstop series FS according to DIN 7865, part 1 and 2, is a permanently flexible sealing profile made of elastomer, SBR or EPDM, that is used to seal construction joints in waterproof concrete structures with high water pressures.

Characteristics / Advantages

- high tensile strength and elongation at break
- high permanent flexibility and high-load bearing capacity
- suitable for water pressure and large settlings
- resistant to all natural media acting aggressively to concrete
- resistant to a wide range of chemical substances (tests required for each additional specific situation)
- resistant to bitumen
- supply of systems for easy handling on site
- vulcanizable by using butt joints on site

Application

- joint sealing in concrete structures
- construction joint sealing system for in-situ concrete

Typical structures

- commercial buildings, cellars, bridges, trough and bridge constructions
- rail tunnels and road tunnels
- water construction plants

Page 1 / 4 Version 03-2019



Standards / Directives

- DIN 18197
- DIN 7865, part 2
- WU- Directives DAfStb
- ZTV-ING, Riz-Ing
- Vulcanizing instructions

Test certificate / Approvals

- latest manufacturer's test certificate
- certificate of conformity DIN 7865
- external monitoring by MPA NRW
- internal monitoring

PRODUCT DATA

Material

- SBR elastomer (styrene butadiene rubber)
- EPDM elastomer (ethylene-propylene-diene monomer)

Colour

black

Packaging

supplied as standard rolls (25 m)


Page 2 / 4 Version 03-2019



MECHANICAL PROPERTIES according to DIN 7865, part 2	
Shore A hardness	62 ± 5
Tear strength	≥ 10 MPa
Elongation at break	≥ 380 %
Compression set	$168h / 23^{\circ}C \le 20\%$ $24h / 70^{\circ}C \le 35\%$
Tear propagation resistance	\geq 8 kN/m
Performance after heat ageing	Shore A hardness change ≤ 8 Tear strength ≥ 9 MPa Elongation at break $\geq 300\%$
Low temperature performance	≤ 90 Shore A
Tension set	≤ 20%
Performance after conditioning in hot bitumen	Residual deformation $< 20\%$ Tear strength ≥ 7 MPa Elongation at break $\ge 300\%$
Performance after ozone ageing	No cracks

Page **3** / **4** Version 03-2019





All dimensions in mm

Page **4** / **4** Version 03-2019